- Excellent adhesion
- Non-flammable
- Extrudes down to -20°F
- UV and mold/mildew resistant
- Permanently flexible
- All weather formula
- Solvent free
- Invisible to UV light
- Tack free in ≤15 minutes; cured in 24-30 hours

Encapsulating compounds that cure even when wet and remain flexible for a permanent seal.

NovaFlex Gutter Seal Paste & Flowable

The non-sag formula of the Paste is ideal for the assembly, repair, and sealing of gutters, while the self-tooling Flowable is perfect for working into miters and corners.

VOC COMPLIANT ENVIRONMENTALLY RESPONSIBLE

CALIFORNIA PROPOSITION 65 COMPLIANT

COLOR CHART

Paste

Flowable

PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range Paste	Performance Range Flowable
Appearance		Paste (Translucent, White, Gray)	Fluid (Translucent, White, Gray, Primer Gray)
Viscosity	Brookfield #7 @ 10 rpm Brookfield #5 @ 10 rpm Brookfield #5 @ 20 rpm	3,500 - 8,000 poises - -	- 700 - 2,500 poises 500 - 1,800 poises
Extrusion Rate	1/8" Orifice @ 50 psi	30 - 80 grams/minute	-
Skin Over Time	3/8" @ 50% RH & 77°F	5 - 15 minutes	30 minutes max.
Through Cure	3/8" @ 50% RH & 77°F	24 - 30 hours	24 - 30 hours

TYPICAL PROPERTIES*

Physical Property	Test Method	Typical Value Paste	Typical Value Flowable
Specific Gravity		1.00 - 1.50	1.00 - 1.50
Tensile Strength	ASTM D412	150 psi	150 psi
Elongation	ASTM D412	500%	500%
Tear Resistance	ASTM D624	30 - 35 pli	-
Shore A Hardness	ASTM D2240	20 +/- 5	20 +/- 5
Service Temperature		-40°F to 400°F (-40°C to 204°C)	-40°F to 400°F (-40°C to 204°C)
Application Temperature		-20°F to 160°F (-29°C to 71°C)	-20°F to 160°F (-29°C to 71°C)
Adhesion Glass Aluminum	ASTM D903	 >15 pli >15 pli	 >15 pli >15 pli

AVAILABLE IN: 10 ounce cartridges and 3 ounce squeeze tubes.

USES: Sealing gutters, downspouts, underdecks, patio covers, carports, and rain carrying systems.